



ANTIQUÉ DORE LIMESTONE

Description:

Consistent gold fine grain background with slight modeling.

Finishes available:

honed, brushed, sand blasted, bush hammered

Physical properties			Class
Apparent density (ASTM C97)	Kg/m3	2,563	II
Absorption coefficient (ASTM C97)	%	0.7	II
Compressive strength (ASTM 170)	MPa	71.2	III
Modulus of rupture (ASTM C99)	MPa	19	III
Flexural strength (ASTM C880)	MPa	10.80	
Abrasion (Hd) (ASTM C241)	mm	15.95	

Recommended Uses
Ashlar masonry:
Elevation, springing course, cornice, sill, base course except severe freeze
Cladding:
Elevation, springing course, cornice, sill, base course except severe freeze
Flooring:
Interior and exterior in warm climate, residential use

Production data		
Maximum project size	sqft	100,000
Slab size	sqft	96" x 56"
Range of thickness feasible	inch	3/8" - 4"