



BATEIG BLUE SANDSTONE

Description:

Light grey background with subtle blue movement

Finishes available:

honed, flamed, sand blasted, bush hammered

Physical properties			Class
Apparent density	Kg/m3	2,700	III
Absorption coefficient	%	5.2	II
Apparent porosity	%	21	
Compressive strength	Mpa	35.5	I
Flexural strength	Mpa	12.8	
Thermal linear expansion coefficient	per °C		
Abrasion Test	mm	21.0	
Impact Test	cm	40	

Recommended Uses
Ashlar masonry:
Elevation, springing course, cornice, sill, base course except severe freeze
Cladding:
Elevation, springing course, cornice, sill, base course except severe freeze
Flooring:
Interior and exterior in warm climate, low commercial traffic

Production data		
Maximum project size	sqft	200,000
Slab size	inch	108" x 60"
Range of thickness feasible	inch	3/8"- 5"