



## BEAUHARNAIS CLAIR LIMESTONE

**Description:**

Fine grain light beige background with thin crystalline calcite veins, glass seam

**Finishes available:**

Honed, polished, patiné

Physical properties			Class
Apparent density	Kg/m3	2,560	III
Porosity	%	2.3	III
Sound propagation speed	m/s	5,200 to 5,500	
Resistance to fixation elements (3cm)	daN	120 to 170	
Compressive strength	Mpa	100 to 120	III
Bending strength	MPa	12 to 16	III
Abrasion Resistance	mm	32 to 37	

Recommended Uses
<b>Ashlar masonry:</b> Elevation, springing course, cornice, sill, base course except severe freeze
<b>Cladding:</b> Elevation, springing course, cornice, sill, base course except severe freeze
<b>Flooring:</b> Interior and exterior in warm climate, medium commercial traffic

Production data		
Maximum project size	sqft	20,000
Slab size	inch	96" x 48"
Range of thickness feasible	inch	3/8"- 2"