



BEAUMANIERE LIGHT LIMESTONE

Description:

Oolitic limestone, light to medium beige, slightly amber. Large copper swirls with occasional fossils.

Finishes available:

Honed, patiné, antique, bush hammered

Physical properties			Class
Apparent density	Kg/m3	2398 to 2460	II
Porosity	%	9 to 11	II
Sound propagation speed	m/s	4,880 to 4,950	
Resistance to fixation elements	daN	180	
Compressive strength	Mpa	57 to 78	III
Bending strength	MPa		
Abrasion Resistance	mm	44 to 48	
Freeze thaw	cycles	>240	

Recommended Uses
Ashlar masonry:
Elevation, springing course, cornice, sill, base course.
Cladding:
Elevation, springing course, string course, sill, base course, coping.
Flooring:
Interior and exterior, residential use.

Production data		
Maximum project size	sqft	20,000
Slab size	inch	84" x 48"
Range of thickness feasible	inch	3/8"- 5"