



CORTON LIMESTONE

Description:

Light beige gold background with occasional veins

Finishes available:

honed, flamed, flamed-brushed, sand blasted, bush hammered

Physical properties			Class
Apparent density (ASTM C97)	Kg/m3	2,721	III
Absorption coefficient (ASTM C97)	%	0.3	III
Porosity	%		
Compressive strength (ASTM 170)	MPa	139.4	III
Modulus of rupture (ASTM C99)	MPa		
Flexural strength (ASTM C880)	MPa		
Abrasion (Hd) (ASTM C241)	mm	33.90	

Recommended Uses
Ashlar masonry:
Elevation, springing course.
Cladding:
Elevation, springing course.
Flooring:
Interior and exterior, heavy commercial traffic

Production data		
Maximum project size	sqft	100,000
Slab size	sqft	120" x 60"
Range of thickness feasible	inch	3/8"- 2"