



## FOSSIL ORO LIMESTONE

**Description:**

Light creamy background with golden brown fossils

**Finishes available:**

honed, patiné, sand blasted, bush hammered

Physical properties			Class
Apparent density (ASTM C97)	Kg/m3	2,618	III
Absorption coefficient (ASTM C97)	%	0.29%	III
Porosity	%		
Compressive strength (ASTM 170)	MPa	91.7	III
Modulus of rupture (ASTM C99)	MPa		
Flexural strength (ASTM C880)	MPa		
Abrasion (Hd) (ASTM C241)	mm	26.40	

Recommended Uses
<b>Ashlar masonry:</b> Elevation, springing course.
<b>Cladding:</b> Elevation, springing course.
<b>Flooring:</b> Interior and exterior, heavy commercial traffic

Production data		
Maximum project size	sqft	100,000
Slab size	sqft	110" x 60"
Range of thickness feasible	inch	3/8"- 2"