



FRENCH BLUE LIMESTONE

Description:

light grey-blue background with blue leafy modeling.

Finishes available:

Honed, polished, flamed, flamed brushed

Physical properties			Class
Apparent density	Kg/m3	2,436	II
Porosity	%	9.6	II
Sound propagation speed	m/s	4810	
Resistance to fixation elements (3cm)	daN		
Compressive strength	Mpa	147	III
Bending strength	MPa		
Abrasion Resistance	mm	0.5	

Recommended Uses
Ashlar masonry:
Elevation, springing course, cornice, sill, base course except severe freeze
Cladding:
Elevation, springing course, cornice, sill, base course except severe freeze
Flooring:
Interior, medium commercial traffic

Production data		
Maximum project size	sqft	30,000
Slab size	inch	104" x 60"
Range of thickness feasible	inch	3/8"- 2"