



GASCOGNE BEIGE LIMESTONE

Description:

Light creamy-beige background with medium to large brown fossils.

Finishes available:

Polished, honed, brushed, sand blasted, bush hammered

Physical properties			Class
Apparent density	Kg/m3	2,478	II
Absorption coefficient	%	3.07	II
Apparent porosity	%	7.62	
Compressive strength	MPa	90	III
Flexural strength	MPa	14	
Thermal linear expansion coefficient	per °C	3.1 x 10 ⁻⁶	
Abrasion Test	mm	3.5	
Impact Test	cm	35	

Recommended Uses
Ashlar masonry: Elevation, springing course.
Cladding: Elevation, springing course.
Flooring: Interior and exterior in warm climate, medium commercial traffic

Chemical properties		
CaO	%	55.76
MgO	%	0.00
K2O	%	0.00
Na2O	%	0.07
SiO2	%	0.06
Fe2O3	%	0.04
Al2O3	%	0.23
P R	%	43.82

Production data		
Maximum project size	sqft	200,000
Slab size	inch	108" x 58"
Range of thickness feasible	inch	3/8" - 2"