



HAUTEVILLE LIMESTONE

Description:

Taupy beige fine grain background with some crystal veins and rust spots.
Occasional fossils

Finishes available:

Honed, polished, flamed, flamed brushed

Physical properties			Class
Apparent density	Kg/m ³	2,680	III
Porosity	%	0.6	III
Sound propagation speed	m/s	5,887	
Resistance to fixation elements (3cm)	daN		
Compressive strength	Mpa	173	III
Bending strength	MPa		
Abrasion Resistance	mm	21.9	
Freeze thaw	cycles	>240	

Recommended Uses
Ashlar masonry: Elevation, springing course.
Cladding: Elevation, springing course.
Flooring: Interior and exterior, heavy commercial traffic

Production data		
Maximum project size	sqft	30,000
Slab size	inch	96 x 48"
Range of thickness feasible	inch	3/8" - 2"