



## LANVIGNES LIMESTONE

**Description:**

Ochre to dark amber background with small fossils. More or less uniform.

**Finishes available:**

Honed, patiné, antique, bush hammered, split

Physical properties			Class
Apparent density	Kg/m <sup>3</sup>	2,140	II
Porosity	%	20.7	II
Sound propagation speed	m/s	4377	
Resistance to fixation elements (3cm)	daN	94	
Compressive strength	Mpa	72	III
Bending strength	MPa	8	III
Abrasion Resistance	mm	30.9	
Freeze thaw	cycles	>240	

Recommended Uses
<b>Ashlar masonry:</b> Elevation, springing course, cornice, sill, base course.
<b>Cladding:</b> Elevation, springing course, string course, sill, base course, coping.
<b>Flooring:</b> Interior and exterior, residential use.

Production data		
Maximum project size	sqft	50,000
Slab size	inch	96" x 52"
Range of thickness feasible	inch	3/8"- 5"