



## MASSANGIS CLAIR LIMESTONE

**Description:**

Light yellow ochre background, fine and medium grain

**Finishes available:**

Honed, patiné, sand blasted, bush hammered

Physical properties			Class
Apparent density	Kg/m <sup>3</sup>	2200 to 2400	II
Porosity	%	10 to 15	II
Sound propagation speed	m/s	4,000 to 4,500	
Resistance to fixation elements (3cm)	daN	100 to 120	
Compressive strength	Mpa	50 to 70	II
Bending strength	MPa	8 to 11	III
Abrasion Resistance	mm	37 to 42	

Recommended Uses
<b>Ashlar masonry:</b> Elevation, springing course, cornice, sill, base course.
<b>Cladding:</b> Elevation, springing course, string course, sill, base course, coping.
<b>Flooring:</b> Interior and exterior, residential use.

Production data		
Maximum project size	sqft	100,000
Slab size	inch	102" x 54"
Range of thickness feasible	inch	3/8"- 20"