



PISTACHE LIMESTONE

Description:

Light green background with large beige fossil

Finishes available:

honed, brushed, sand blasted, bush hammered

Physical properties			Class
Apparent density (ASTM C97)	Kg/m3	2,699	III
Absorption coefficient (ASTM C97)	%	0.4	III
Porosity	%	0.9	
Compressive strength (ASTM 170)	MPa	142.6	III
Modulus of rupture (ASTM C99)	MPa		
Flexural strength (ASTM C880)	MPa	16.7	
Abrasion (Hd) (ASTM C241)	mm		

Recommended Uses
Ashlar masonry: Elevation, springing course.
Cladding: Elevation, springing course.
Flooring: Interior and exterior, heavy commercial traffic

Production data		
Maximum project size	sqft	100,000
Slab size	sqft	108" x 56"
Range of thickness feasible	inch	3/8" - 2"