



POMPIGNAN LIMESTONE

Description:

Fine grain background ranging from light grey, taupe to charcoal grey .

Finishes available:

Honed, polished, flamed, flamed brushed

Physical properties			Class
Apparent density	Kg/m3	2,687	III
Porosity	%	0.5	III
Sound propagation speed	m/s	5650 to 5747	
Resistance to fixation elements (3cm)	daN		
Compressive strength	Mpa	127	III
Bending strength	MPa		
Abrasion Resistance	mm		
Freeze thaw	cycles	>240	

Recommended Uses
Ashlar masonry:
Elevation, springing course.
Cladding:
Elevation, springing course.
Flooring:
Interior and exterior, heavy commercial traffic

Production data		
Maximum project size	sqft	50,000
Slab size	inch	96 x 48"
Range of thickness feasible	inch	3/8"- 2"