



## ROCHERON BEIGE LIMESTONE

**Description:**

Beige background slightly speckled. Leafy pattern with styloliths, fossils and thin calcite veins.

**Finishes available:**

Honed, polished, flamed, patiné

Physical properties			Class
Apparent density	Kg/m <sup>3</sup>	2600 to 2700	III
Porosity	%	< 2	III
Sound propagation speed	m/s	5,800 to 6,000	
Resistance to fixation elements (3cm)	daN	160 to 190	
Compressive strength	Mpa	110 to 150	III
Bending strength	MPa	10 to 15	III
Abrasion Resistance	mm	22 to 25	

Recommended Uses
<b>Ashlar masonry:</b> Elevation, springing course.
<b>Cladding:</b> Elevation, springing course.
<b>Flooring:</b> Interior and exterior in light freezing area, heavy commercial traffic

Production data		
Maximum project size	sqft	100,000
Slab size	inch	102" x 54"
Range of thickness feasible	inch	3/8"- 2"