



SAINT MARC DORE LIMESTONE

Description:

Oolitic limestone, creamy gold background, medium grain.

Finishes available:

Honed, patiné, antique, bush hammered

Physical properties			Class
Apparent density	Kg/m ³	2,340	II
Porosity	%	11	II
Sound propagation speed	m/s	4568	
Resistance to fixation elements (3cm)	daN	128	
Compressive strength	Mpa	77	III
Bending strength	MPa	5	
Abrasion Resistance	mm	33.2	
Freeze thaw	cycles	>240	

Recommended Uses
Ashlar masonry: Elevation, springing course, cornice, sill, base course.
Cladding: Elevation, springing course, string course, sill, base course, coping.
Flooring: Interior and exterior, residential use.

Production data		
Maximum project size	sqft	5,000
Slab size	inch	88" x 42"
Range of thickness feasible	inch	3/8" - 5"