



SAINT MARC JAUNE LIMESTONE

Description:

Oolitic limestone, Ochre to dark amber background.

Finishes available:

Honed, patiné, antique, bush hammered

Physical properties			Class
Apparent density	Kg/m3	2,340	II
Porosity	%	11	II
Sound propagation speed	m/s	4525	
Resistance to fixation elements (3cm)	daN	130	
Compressive strength	Mpa	77	III
Bending strength	MPa		
Abrasion Resistance	mm	33.1	
Freeze thaw	cycles	>240	

Recommended Uses
Ashlar masonry: Elevation, springing course, cornice, sill, base course.
Cladding: Elevation, springing course, string course, sill, base course, coping.
Flooring: Interior and exterior, residential use.

Production data		
Maximum project size	sqft	40,000
Slab size	inch	96" x 48"
Range of thickness feasible	inch	3/8"- 5"