



SAINT MARTIN LIMESTONE

Description:

Fine grain background ranging from light grey, taupe to charcoal grey .

Finishes available:

Honed, polished, flamed, flamed brushed

| Physical properties | | |
|---------------------------------------|--------|-------|
| Apparent density | Kg/m3 | 2,662 |
| Porosity | % | 0.56 |
| Sound propagation speed | m/s | 5680 |
| Resistance to fixation elements (3cm) | daN | 231 |
| Compressive strength | Mpa | 116 |
| Bending strength | MPa | |
| Abrasion Resistance | mm | 29.1 |
| Freeze thaw | cycles | >240 |

| Recommended Uses |
|---------------------------------------------------------|
| Ashlar masonry: |
| Elevation, springing course, cornice, sill, base course |
| Cladding: |
| Elevation, springing course, cornice, sill, base course |
| Flooring: |
| Interior and exterior, medium commercial traffic |

| Production data | | |
|-----------------------------|------|-----------|
| Maximum project size | sqft | 50,000 |
| Slab size | inch | 96 x 48" |
| Range of thickness feasible | inch | 3/8" - 2" |