



HAUSSMANN
NATURAL STONE

SAINTE CROIX LIMESTONE

Description:

creamy white background with medium to large fossils. Some rust spots

Finishes available:

Honed, polished, patiné, flamed, flamed brushed

Physical properties		
Apparent density	Kg/m3	2,560
Porosity	%	5.1
Sound propagation speed	m/s	5335
Resistance to fixation elements (3cm)	daN	
Compressive strength	Mpa	105
Bending strength	MPa	
Abrasion Resistance	mm	27.5

Recommended Uses
Ashlar masonry: Elevation, springing course, cornice, sill, base course except severe freeze
Cladding: Elevation, springing course, cornice, sill, base course except severe freeze
Flooring: Interior and exterior in warm climate, medium commercial traffic

Production data		
Maximum project size	sqft	100,000
Slab size	inch	96 x 48"
Range of thickness feasible	inch	3/8" - 2"