



VENDOME LIMESTONE

Description:

Creamy beige background with regular fin fossiling.

Finishes available:

Honed, patiné, sand blasted, bush hammered

Physical properties			Class
Apparent density	Kg/m3	2,490	II
Absorption coefficient	%	2	III
Apparent porosity	%		
Compressive strength	MPa	108.8	III
Flexural strength	MPa		
Thermal linear expansion coefficient	per °C		
Abrasion Test	mm		
Impact Test	cm		

Recommended Uses
Ashlar masonry: Elevation, springing course, cornice, sill, base course.
Cladding: Elevation, springing course, string course, sill, base course, coping.
Flooring: Interior and exterior, residential and medium commercial traffic

Production data		
Maximum project size	sqft	100,000
Slab size	inch	96" x 48"
Range of thickness feasible	inch	3/8"- 2"