



BUFFON 3 LIMESTONE

Description:

Light cream beige background with golden grains.

Finishes available:

Honed, patiné, antique, bush hammered, split

Physical properties			Class
Apparent density	Kg/m3	2,560	III
Porosity	%	3	III
Sound propagation speed	m/s	5600	
Resistance to fixation elements (3cm)	daN		
Compressive strength	Mpa	168	III
Bending strength	MPa		
Abrasion Resistance	mm	25.1	
Freeze thaw	cycles		

Recommended Uses
Ashlar masonry: Elevation, springing course, cornice, sill, base course.
Cladding: Elevation, springing course, string course, sill, base course, coping.
Flooring: Interior and exterior, heavy traffic

Production data		
Maximum project size	sqft	150,000
Slab size	inch	96" x 52"
Range of thickness feasible	inch	3/8" - 5"